

# MasterKure® 107 (Formerly known as Masterkure® 107)

Water based concrete curing compound, white pigmented for solar reflectance

## DESCRIPTION

**MasterKure® 107** incorporates a white pigment which at recommended coverage rates gives a daylight reflectance value of 60-80%. This permits a high curing efficiency to be maintained even in conditions of intense ambient light.

**MasterKure® 107** is a solvent free, membrane forming wax emulsion, suitable for spray application to freshly poured concrete.

The resultant film retains sufficient moisture in the concrete to ensure full hydration of the cement; essential for optimum strength development. Membrane cured concrete is typically harder and exhibits a dust free surface with a reduced incidence of drying shrinkage cracks.

## PRIMARY USES

As a more effective and economical alternative to hessian and water and polythene curing regimes. Suitable for use on all concrete surfaces.

## ADVANTAGES

- Eliminates the need for water
- Single application
- Promotes a harder dust free surface
- Cured film is clear and water repellent
- Reduces drying shrinkage
- High curing efficiency
- Reduced labour costs
- Water based
- Solar reflective

## PACKAGING

**MasterKure® 107** is available in 210 litre drums.

## TYPICAL PROPERTIES

Appearance	White liquid
Specific gravity	0.9
Flashpoint	Not applicable
Finished film appearance	white solar reflective, tack free, water repellent
Water retention (ASTM C309):	Pass
Drying time (ASTM C309):	3 hours, PASS

## STANDARDS

ASTM C309 Type 2 Class A

## DIRECTIONS FOR USE

The compound should be spray applied as evenly as possible to the freshly placed concrete.

For horizontal surfaces the **MasterKure® 107** should be applied as soon as the initial surface sheen has disappeared from the concrete face. In the case of formed concrete, the **MasterKure 107** should be applied immediately on removal of the formwork. To assist breakdown of the **MasterKure 107** film on the vertical and formed surfaces, it is essential to dampen down the concrete with clean water prior to application.

## COVERAGE

The recommended rate of application is 5-6 square metres per litre. This corresponds to that which **MasterKure® 107** has been tested, and at which it attains the claimed degree of curing efficiency. In favourable conditions such as shaded interior surfaces, adequate curing can be achieved with extended coverage rates.

## FILM BREAKDOWN

The time for deterioration of the membrane is dependent on a number of variables, which include film thickness, degree of exposure to weathering, traffic, UV light, and the porosity of the substrate concrete.



We create chemistry

# MasterKure<sup>®</sup> 107 (Formerly known as Masterkure<sup>®</sup> 107)

## SUBSEQUENT SURFACE FINISHES

It is important that the complete removal of the **MasterKure<sup>®</sup> 107** should be ensured prior to the application of any surface finish or additional treatment. It is recommended that where the concrete is to receive a coating or the application of tiles, the use of **MasterKure<sup>®</sup> 181** is considered.

**MasterKure<sup>®</sup> 181** is a resin based non-degrading curing membrane meeting the requirements of ASTM C-309 Type 1 Class B. It is additionally formulated to act as a primer for many finishes or to seal concrete surfaces and provide a degree of abrasion to flatwork.

## STORAGE

Shelf life is up to 12 months when stored under cover, out of direct sunlight and protected from extremes of temperature.

Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

## HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention. Reseal containers after use. Use in well ventilated areas and avoid inhalation.

## NOTE

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

## QUALITY AND CARE

All products originating from BASF Construction Chemicals South Africa are manufactured under a management system independently certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, 2008.

\* Properties listed are based on laboratory controlled tests.

® = Registered trademark of the BASF-Group in many countries.

## STATEMENT OF RESPONSIBILITY

The technical information and application advice given in this BASF publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a particular use or application and no warranty as to its accuracy, reliability or completeness either expressed or implied is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.

## NOTE

Field service where provided does not constitute supervisory responsibility. Suggestions made by BASF either orally or in writing may be followed, modified or rejected by the owner, engineer or contractor since they, and not BASF, are responsible for carrying out procedures appropriate to a specific application.